

KÖSTER Repair Mortar NC

Technical guideline / Article number **5.035**
Issued: July 25, 2011

Fiber reinforced repair, concrete replacement and finishing mortar with high chemical and mechanical resilience

Features

KÖSTER Repair Mortar NC is a repair mortar and plaster with excellent workability. It has a high adhesion to old and new mineral building material substrates.

KÖSTER Repair Mortar NC is characterised by high chemical and mechanical resistance and compressive strength. It is fiber reinforced. It is ideally suited as substrate preparation for corrosion protection with KÖSTER PSM or KÖSTER Silicate Mortar, for example in industrial chimneys, sewer systems, or other concrete structures which are exposed to low pH environments.

Technical data

Compressive strength (7 days)	> 35 N / mm ²
Compressive strength (28 days)	>45 N / mm ²
Bending tensile strength (7 days)	approx. 3.5 N / mm ²
Bending tensile strength (28 days)	approx. 4.5 N / mm ²
Modulus of Elasticity	approx. 15000 N / mm ²
Shrinkage	< 0.5 mm / m
Specific gravity of mortar	approx. 1.89 kg / l
Max. layer thickness (as plaster) per layer	5 cm
Pot life (20° C)	approx. 45 min.

Field of application

KÖSTER Repair Mortar NC can be used for structurally relevant repair and touch up of voids, and for levelling of concrete defects.

The material is especially suited as a repair mortar for use in structural members which are exposed to exceptional chemical and mechanical stresses such as for example in agricultural construction, chimneys with corrosive flue gas conditions, or wastewater applications.

Substrate preparation

The surface has to be sound and solid, free of oil and grease, free of formwork separating agents, residual adhesions and cement residue. The material can be applied to all concrete substrates.

The pull off strength of the substrate must have a minimum of 1.5 N / mm². Directly before the application, pre-wet the substrate so that it is matt moist. Avoid standing water. Absorptive and salt contaminated substrates are to be primed with approximately 200 g/m² of KÖSTER Polysil® TG 500.

Mixing

Mix 25 kg of KÖSTER Repair Mortar NC with 4.2 l water. Place $\frac{3}{4}$ of the liquid into a mixing vessel of sufficient size and add the powder in portions while continually mixing with a slow rotating double paddle electrical mixer. Add the remaining liquid as needed during mixing to adjust the mortar to the desired consistency. Mix until a homogeneous, lump-free consistency is reached. Minimum mixing time is 3 minutes. If applying the maximum layer thickness of 5 cm the surface should also receive a scratch coat made from KÖSTER Repair Mortar NC with 5% KÖSTER SB Bonding Emulsion added to the mixing water.

Application

The mortar has a pot life of approx. 45 min. Apply KÖSTER Repair Mortar NC using customary mason's tools or using suited spraying equipment. Application of a second layer can be started after approximately 24 hours.

Consumption

Approx. 1.9 kg / l void as repair mortar

Approx. 19 kg / m² per cm of layer thickness of the plaster

Cleaning of tools

Clean tools immediately after use with water.

Packaging

25 kg bag

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

Storage

Store the material dry; when stored in originally sealed packages it is can be stored for 6 months.

Safety precautions

Wear protective gloves and goggles.

Technical guidelines cited

KÖSTER Polysil® TG 500	4.011
KÖSTER PSM	5.18
KÖSTER Silicate Mortar	5.15
KÖSTER Bonding Emulsion „Concentrate“	2.11

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.