



## **KÖSTER TPO 1.8**

**Technical Data Sheet RT 818** 

Prod. code RT 919 003

Prod. code RT 919 004

Issued: 2023-09-09

#### **Test Reports/Certificates**

EPD-KBC-20160014-IBC1-DE Environmental Product Declaration according to the ISO 14025 and EN 15804. 
Official Test Report according to 1200/057/15 DIN EN 13956 MPA Braunschweig, 
Official Test Report according to 5278/015/14 DIN EN 13967 MPA Braunschweig, 
Certificate of conformity of the factory production control 0761-CPR-0422 MPA Braunschweig, 
Certificate of conformity of the factory production control 0761-CPR-0423 MPA Braunschweig, 
Official Test Report according to FLL 19/16 Hochschule Weihenstephan, 
Fish test A14-02548 BMG Zürich, 
Official Test Report according to ETAG 006 4/2015 I.F.I. Aachen

# TPO Roofing and Waterproofing membrane with centrally embedded glass fleece

#### **Features**

- Plastic waterproofing membrane made of high quality thermoplastic polyolefins based on polyethylene (PE)
- central glass fleece insert
- uniform material quality (no difference between upper and lower side)
- homogeneous seam bonding with hot air welding
- temperature and weather resistant
- aging and rot resistant
- high cold flexibility (≤ -50°C)
- UV-stable
- root resistant
- compatible with bitumen
- compatible with polystyrene
- suitable for all types of insulation
- resistant against normal mechanical stresses
- resistant to microorganisms and rodent attack
- environmentally friendly
- free of softeners and chlorine
- safe for health, water, soil, and plants
- recyclable

#### **Technical Data**

Refer to last page

### **Fields of Application**

KÖSTER TPO Roofing and Waterproofing Membranes are used to waterproof unventilated and ventilated flat roofs, pitched roofs, green roofs, terraces, balconies, roof gardens and underground garages with ballast and in cases of direct exposure to weathering. KÖSTER TPO Roofing and Waterproofing Membranes can be used for the waterproofing of basements, wet rooms and tanks.

#### **Application**

Please refer to the TPO Installation Instructions and the Technical Manual for TPO of KÖSTER BAUCHEMIE AG for correct application of KÖSTER TPO Roofing and Waterproofing Membranes.

#### **Packaging**

RT 818 025	1.8 mm x 0.25 m x 20 m
RT 818 035	1.8 mm x 0.35 m x 20 m
RT 818 052	1.8 mm x 0.525 m x 20 m
RT 818 075	1.8 mm x 0.75 m x 20 m
RT 818 105	1.8 mm x 1.05 m x 20 m
RT 818 150	1.8 mm x 1.50 m x 20 m
RT 818 210	1.8 mm x 2.10 m x 20 m

### Related products

KÖSTER Contact Adhesive	Prod. code RT 102
KÖSTER TPO 2.0 U	Prod. code RT 820 U
KÖSTER External Corner light grey 90	Prod. code RT 901 001
degrees	
KÖSTER Internal Corner light grey 90	Prod. code RT 902 001
degrees	
KÖSTER Round Corner Patch light grey	Prod. code RT 903 001
KÖSTER TPO Metal Composite Sheet	Prod. code RT 910 002
light grey	
KÖSTER TPO Metal Composite Coil light	Prod. code RT 910 030
arov	

KÖSTER Wall connection profile 60 mm

KÖSTER Bar for membrane fastening

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

KÖSTER TPO 1.8 1/2



	KÖSTER BA	UCHEMIE AG	
	Dieselstraße 1-	10, 26607 Aurich	
	_		
	KÖSTE	R TPO 1.8	
	EN 13956 07	761-CPR-0422	
0761	EN 13967 07	761-CPR-0423	
15	TPO (PE) roofing and wat	erproofing membrane with	
	central glass	s fleece insert	
Length according to DIN EN 1848-2	20 m (65´ 7 3/8")		
Width according to DIN EN 1848-2 metric	2.10; 1.50; 1.05; 0.75; 0.525; 0.35; 0.25		
Width according to DIN EN 1848-2 standard	6´10 5/8", 4´11 5/8", 3´5 3/8", 2´5 1/2", 1´8 5/8", 1´1 3/4", 9 7/8"		
Effective thickness according to DIN EN 1849-2	1.8 mm (71 mil)		
	DIN EN 13956: 2012	DIN EN 13967:2012	
	waterproofing of flat and sloped	Vapor Barrier Type T	
	roofs. Application by loose laying		
	with ballast or mechanical		
	fastening		
Perignation according DIN SPEC 20000 201 / 20000 200	DE/E1 EDO DV E OV 1 9	DA EDO DV E GV 1 9	
Designation according DIN SPEC 20000-201 / 20000-202	DE/E1-FPO-BV-E-GV-1,8	BA-FPO-BV-E-GV-1,8	
Color	light grey	light grey	
Visible Defects according to DIN EN 1850-2	free from visible defects	free from visible defects	
Straightness according to DIN EN 1848-2	≤ 50 mm (1 7/8")	≤ 50 mm (1 7/8")	
Flatness according to DIN EN 1848-2  Mass per unit area according to DIN EN 1849-2	$\leq$ 10 mm (3/8") 1740 g /m <sup>2</sup> (5.7 oz/ft <sup>2</sup> )	1740 g /m² (5.7 oz/ft²)	
		9 (	
Water tightness according to DIN EN 1928 (Method B)	400 kPa/24h watertight	400 kPa/72h watertight watertight (Method A)	
Exposure to liquid chemicals, including water according to DIN EN 1847	passed (Method B)	watertight (Method A)	
Exposure to external fire according to DIN CEN/TS 1187; DIN	Broof(t1) <sup>1)</sup>		
4102-7; DIN EN 13501-5		-	
Reaction to fire according to EN 13501-1	Class E	Class E	
Resistance to hail according to DIN EN 13583	Class L	Class L	
Rigid substrate	≥ 25 m/s (56 mph)	_	
Soft substrate	≥ 40 m/s (89 mph)	_	
Peel resistance of the overlap according to	≥ 500 N/50 mm (57 lb/in)		
DIN EN 12316-2	2 300 14/30 11111 (37 15/111)	_	
Shear resistance of the overlap according to DIN EN	Failure beyond the overlap	Failure beyond the overlap	
12317-2	Tanare beyond the overlap	Tallare beyond the evenap	
Water vapor diffusion resistance according to DIN EN 1931	$\mu = 85,000$	$\mu = 85,000$	
Tensile characterisitcs according to DIN EN 12311-2	μ = 60,000	μ = 00,000	
Tensile strength	≥ 7 N/mm² (Method B)	≥ 7 N/mm² (Method B)	
Elongation at break	≥ 500 % (Method B)	≥ 500 % (Method B)	
Resistance to shock loads according to DIN EN 12691		_ 100 /0 (osilod b)	
Method A	≥ 750 mm (29.5")	≥ 750 mm (29.5")	
Method B	≥ 1250 mm (49.2")	≥ 1250 mm (49.2")	
Resistance to static loading according to DIN EN 12730			
Method A	≥ 20 kg (44 lbs)	≥ 20 kg (44 lbs)	
Method B	≥ 20 kg (44 lbs)	≥ 20 kg (44 lbs)	
Tear continuation resistance according to DIN EN 12310-2	≥ 200 N (45 lbs)	≥ 200 N (45 lbs)	
Root penetration resistance 2)	given	-	
Dimensional stability according to DIN EN 1107-2	≤ 0.2 %	≤ 0.2 %	
Folding at low temperatures	≤ - 50°C	-	
according to DIN EN 495-5			
Behavior under UV irradiation, elevated temperatures, and	passed: Level 0	-	
water according to DIN EN 1297 (1000 h)	·		
Ozone resistance according to DIN EN 1844	passed	-	
Exposure to bitumen according to DIN EN 1548	passed	watertight	
Durabilty against heat storage	watertight	watertight	
according to DIN EN 1296, DIN EN 1928 (Method A)	]	-	
Tear resistance (nail shank) according to DIN EN 12310-1	≥ 500 N (112.4 lbs)	≥ 500 N (112.4 lbs)	
1) Requirements are met for roofs tested by KÖSTER in Germany	Eurthor information can be requested from	om KÖCTED 2) Applies only to groop	

<sup>1)</sup> Requirements are met for roofs tested by KÖSTER in Germany. Further information can be requested from KÖSTER. 2) Applies only to green roofs

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

KÖSTER TPO 1.8 2/2